

品名	目数 (根)	线径 (mm)	开口率	厚度 (μm)				强度指数※
				原网	扎压			
					轻扎	中扎	重扎	
BS-500/16	500	0.016	47%	36 ± 2	25 ± 2	20 ± 1	16 ± 1	0.50
BS-500/19	500	0.019	39%	41 ± 2	30 ± 2	25 ± 1	19 ± 1	0.71
BS-400/19	400	0.019	49%	39 ± 2	34 ± 2	30 ± 1	23 ± 1	0.57
BS-400/23	400	0.023	41%	55 ± 2	40 ± 2	35 ± 1	25 ± 1	0.83
BS-400/25	400	0.025	37%	57 ± 2	49 ± 2	40 ± 1	30 ± 1	0.98
★ BS-325/28	325	0.028	41%	62 ± 2	55 ± 2	47 ± 1	40 ± 1	1.00
BS-325/30	325	0.030	38%	62 ± 2	60 ± 2	47 ± 2	42 ± 1	1.15
BS-300/30	300	0.030	42%	68 ± 2	59 ± 2	50 ± 2	45 ± 1	1.06
BS-270/35	270	0.035	39%	77 ± 2	70 ± 2	58 ± 2	40 ± 2	1.30
BS-250/30	250	0.030	50%	62 ± 2	58 ± 2	50 ± 2	45 ± 2	0.88
★ BS-250/35	250	0.035	43%	78 ± 2	64 ± 2	57 ± 2	55 ± 2	1.20
BS-250/40	250	0.040	37%	90 ± 3	86 ± 2	72 ± 2	67 ± 2	1.57
★ BS-200/40	200	0.040	47%	82 ± 3	77 ± 2	72 ± 2	63 ± 2	1.26

品名	目数 (根)	线径 (mm)	开口率	厚度 (μm)				强度指数※
				原网	扎压			
					轻扎	中扎	重扎	
★ MS-730/13	730	0.013	40%	28 ± 2	20 ± 1	18 ± 1	15 ± 1	0.63
★ MS-640/15	640	0.015	39%	35 ± 2	25 ± 1	21 ± 1	17 ± 1	0.73
MS-500/16	500	0.016	47%	36 ± 2	25 ± 2	20 ± 1	15 ± 1	0.65
MS-500/19	500	0.019	39%	41 ± 2	36 ± 2	25 ± 1	20 ± 1	0.93
MS-400/19	400	0.019	49%	42 ± 2	30 ± 2	23 ± 1	18 ± 1	0.74
★ MS-400/23	400	0.023	41%	55 ± 2	40 ± 1	35 ± 1	26 ± 1	1.08
MS-325/24	325	0.024	48%	51 ± 2	44 ± 2	38 ± 2	25 ± 2	0.96
★ MS-325/28	325	0.028	41%	56 ± 2	51 ± 2	45 ± 2	39 ± 2	1.30
MS-250/30	250	0.030	50%	62 ± 2	58 ± 2	45 ± 2	28 ± 1	1.15

品名	目数 (根)	线径 (mm)	开口率	厚度 (μm)				强度指数※
				原网	扎压			
					轻扎	中扎	重扎	
SHS-380/14	380	0.014	62%	32 ± 2	26 ± 2	20 ± 1	14 ± 1	0.96
SHS-360/16	360	0.016	60%	36 ± 3	32 ± 2	21 ± 1	16 ± 1	1.19
SHS-325/16	325	0.016	63%	35 ± 3	32 ± 2	20 ± 1	18 ± 1	1.08
SHS-290/20	290	0.020	60%	45 ± 3	36 ± 2	30 ± 1	20 ± 1	1.50
SHS-230/25	230	0.025	60%	55 ± 3	45 ± 2	35 ± 1	27 ± 1	1.86
HS-360/16	360	0.016	60%	36 ± 3	32 ± 2	20 ± 1	16 ± 1	1.05
HS-325/16	325	0.016	63%	35 ± 2	32 ± 2	20 ± 1	17 ± 1	0.95
HS-290/20	290	0.020	60%	45 ± 2	36 ± 2	30 ± 1	20 ± 1	1.32
HS-250/20	250	0.020	65%	44 ± 2	37 ± 2	30 ± 1	18 ± 1	1.14
HS-230/25	230	0.025	60%	55 ± 2	40 ± 2	30 ± 2	27 ± 1	1.64

品名	目数 (根)	线径 (mm)	开口率	厚度 (μm)				强度指数※
				原网	扎压			
					轻扎	中扎	重扎	
★★ HS-D 650/14	650	0.014	41%	34 ± 2			23 ± 2	1.45
★★ HS-D 500/19	500	0.019	39%	45 ± 2			25 ± 1	2.05
★★ HS-D 360/25	360	0.025	42%	59 ± 2		41 ± 2	29 ± 1	2.56

品名	目数 (根)	线径 (mm)	开口率	厚度 (μm)				强度指数※
				原网	扎压			
					轻扎	中扎	重扎	
3D-400-66	400	0.023	41%	66 ± 3				
3D-325-77	325	0.028	41%	77 ± 3				
3D-250-85	250	0.030	50%	85 ± 3				
3D-200-115	200	0.040	47%	115 ± 4				
3D-165-126	165	0.045	50%	126 ± 5				
3D-80-225	80	0.080	56%	225 ± 5				

※ 强度指数是以BS325/28的强度为基准，与之相比的参考值。详细情况请参考强度延伸数据。

※ 2014年5月至现在的规格表。上记规格为当社产品的一部分。

为实现高品质丝网印刷，特推荐[A标准 (★)]及[SA标准 (★★)]。